



AMERON
INTERNATIONAL

FIBERGLASS - COMPOSITE PIPE GROUP

Bondstrand® Guide Specifications

Bondstrand 5000 Pipe and Fittings

Vinylester reinforced thermosetting resin pipe
for plant piping fiberglass piping systems

Scope

This specification defines the reinforced thermosetting resin (RTR) piping system to be used in those sections of Plant Piping General Services calling for fiberglass piping systems.

References, Quality Assurance

References are made to other standards and tests which are a part of this section. Where conflict exists between the requirements of this specification and listed references, the specification shall prevail.

Physical and Mechanical Properties

Pipe Property	Units	70°F 21°C		170°F 77°C		ASTM Method
		2"-6"	8"-16"	2"-6"	8"-16"	
Nominal Pipe Size		2"-6"	8"-16"	2"-6"	8"-16"	
Circumferential						
Tensile stress at weeping	10 ³ psi MPa	24.00 138.00	24.00 138.00	- -	- -	D1599
Tensile modulus	10 ⁶ psi GPa	3.70 25.50	3.13 21.60	2.90 20.00	2.32 16.00	
Poisson's ratio		0.28	0.45	0.35	0.66	D2105
Longitudinal						
Tensile strength	10 ³ psi MPa	12.00 82.70	7.00 48.30	8.00 55.20	5.50 37.90	D2105
Tensile modulus	10 ⁶ psi GPa	2.00 13.80	1.45 10.00	1.40 9.70	1.00 6.89	D2105
Poisson's ratio		0.20	0.35	0.26	0.43	D2105
Beam apparent Elastic modulus	10 ⁶ psi GPa	1.70 11.70	1.40 9.65	1.45 10.10	.44 3.00	D2925
Hydrostatic design basis (cyclic)	10 ³ psi MPa	8.00 55.20	6.00 41.40	- -	- -	D2992
Thermal conductivity Pipe wall	Btu•in/(hr•ft ² •°F) W/m•°C	2.00 0.28	2.00 0.28	- -	- -	C177
Thermal expansion Linear	10 ⁻⁶ in/in/°F 10 ⁻⁶ mm/mm°C	10.00 18.00	10.00 18.00	- -	- -	D696
Flow coefficient	Hazen-Williams	150.00	150.00	-	-	
Absolute roughness	10 ⁻⁶ ft 10 ⁻⁶ m	17.40 5.30	17.40 5.30	-	-	
Specific gravity	-	1.80	1.80	-	-	D792
Density	lb/in ³	0.07	0.07	-	-	

Performance Requirements

ISO-9001



DNV
CERTIFICATED FIRM

The pipe shall be manufactured in accordance with ASTM D2996 Specification for RTRP. When classified under ASTM D2310, the pipe shall meet Type I, Grade 2 and Class E (RTRP-12ED) for 2" through 16" nominal pipe sizes.

Pipe shall be rated for a minimum internal pressure of 150 psig at 200°F in sizes 1" through 16" and shall have full vacuum capability at 80°F in sizes 1" through 10" when installed above ground.

Materials

Pipe Construction

Filament-wound fiberglass reinforced vinylester resin pipe shall be Bondstrand 5000 as manufactured by Ameron International Fiberglass Pipe Group, or approved equal. The pipe shall have an integral corrosion barrier, nominally 50 mils thick, constructed with the same vinylester resin as the pipe structural wall. Non-reinforced liners or corrosion barriers shall not be allowed due to potential for fracturing during lower temperature, transportation, and installation.

Structural wall

The pipe shall have the following nominal wall thickness:

Pipe end preparation options

The piping manufacturer will provide 20' or 40' RL joints, if the contractor requests them, in sizes 2" through 6" to reduce field labor assembly time in those sections of the system where longer joint lengths may be employed. In addition, the pipe manufacturer will provide pipe joints with the spigot ends already prepared for adhesive application to reduce field labor time on all pipe sizes (1"-16") along with factory installed bells or couplings.

Pipe Diameter	Nominal Wall Thickness	
	inches	mm
1	.140	3.5
1.5	.140	3.5
2	.123	3.1
3	.126	3.2
4	.151	3.8
6	.181	4.6
8	.226	5.7
10	.226	5.7
12	.226	5.7
14	.250	6.4
16	.269	6.8

Fittings

It is important to maintain compatibility of fittings, piping and adhesives to ensure that the system performs as specified. Pipe, fittings and adhesive shall be supplied by the same manufacturer.

Filament-wound fittings

Fittings in 1" through 16" nominal sizes shall be filament-wound with a reinforced resin-rich liner of equal or greater thickness than the pipe liner and shall be manufactured with the same resin type as the pipe.

Compression Molded Fittings

Compression molded fittings in sizes 2" through 6" nominal sizes may be used in services at or below 150°F. Where fast closure of valves may produce surges (water hammer), filament wound fittings will be used.

Contact molded, spray up or hand lay-up fittings shall not be allowed.

Testing

Inspection and testing of the piping will be performed in accordance with the requirements of ANSI B31.1. Hydrostatic testing of all installed piping shall be performed with water at 1½ times the design pressure of the lowest rated piping system component.

Test and repair procedures

The RTRP manufacturer will provide test and repair procedures in the event field repairs are required.

Installation

Installation procedures and techniques as well as system design criteria including burial, anchoring, guiding and supporting the pipe shall be in accordance with manufacturer's recommendations.

Piping system installers and fitters will be trained by a direct factory employee of the piping system manufacturer and certified by the trainer prior to system assembly in the field.

Important Notice



This literature and the information and recommendations it contains are based on data reasonably believed to be reliable. However, such factors as variations in environment, application or installation, changes in operating procedures, or extrapolation of data may cause different results. Ameron makes no representation or warranty, express or implied, including warranties of merchantability or fitness for purpose, as to the accuracy, adequacy or completeness of the recommendations or information contained herein. Ameron assumes no liability whatsoever in connection with this literature or the information or recommendations it contains. Product specifications are subject to change.

FIBERGLASS - COMPOSITE PIPE GROUP - HEADQUARTERS

P.O. Box 801148 • Houston, TX 77280 • Tel: (713) 690-7777 • Fax: (713) 690-2842 • <http://www.ameron.com>

Asia
Ameron (Pte) Ltd.
No. 7A, Tuas Avenue 3
Singapore 639407
Tel: 65 861 6118
Fax: 65 862 1302/861 7834

Europe
Ameron B.V.
J.F. Kennedylaan 7
4191 MZ Geldermalsen
The Netherlands
Tel: +31 345 587 587
Fax: +31 345 587 561

Americas
P.O. Box 878
Burkburnett, TX 76354
Tel: (940) 569-1471
Fax: (940) 569-2764

Composites
P.O. Box 71370
11 McBride Street
Newnan, Georgia 30263
Tel: (770) 253-2000
Fax: (770) 253-9234

Centron International
P.O. Box 490
600 FM 1195 South
Mineral Wells, Texas 76068
Tel: (940) 325-1341
Fax: (940) 325-9681